SCIENTIFIC REPORTS

Received: 24 January 2017 Accepted: 22 June 2017 Published online: 28 July 2017

OPEN Emergence of superconductivity in doped H₂O ice at high pressure

José A. Flores-Livas¹, Antonio Sanna ², Miglė Graužinytė¹, Arkadiy Davydov², Stefan Goedecker¹ & Miguel A. L. Margues³

We investigate the possibility of achieving high-temperature superconductivity in hydrides under pressure by inducing metallization of otherwise insulating phases through doping, a path previously used to render standard semiconductors superconducting at ambient pressure. Following this idea, we study H₂O, one of the most abundant and well-studied substances, we identify nitrogen as the most likely and promising substitution/dopant. We show that for realistic levels of doping of a few percent, the phase X of ice becomes superconducting with a critical temperature of about 60K at 150GPa. In view of the vast number of hydrides that are strongly covalent bonded, but that remain insulating up to rather large pressures, our results open a series of new possibilities in the quest for novel hightemperature superconductors.

The theoretical prediction¹ and subsequent experimental discovery² of superconductivity in H₃S at 200 GPa, with the record critical temperature $(T_{\rm C})$ of 203 K, rekindled the century-old dream of a room temperature superconductor. The mechanism for superconductivity is clearly understood within the strong coupling theory of Bardeen, Cooper, and Schrieffer³ and the high $T_{\rm C}$ arises from the strong electron-phonon coupling due to the peculiar electronic structure of this system under pressure⁴⁻⁹. The aim of this research effort is to better understand how high critical temperatures can be achieved and if the same mechanisms can work at lower pressures and/or even higher (room temperature) T_c in other materials. In this quest for novel high- T_c superconductors, many other materials have been proposed. As the presence of hydrogen seems to be fundamental to reach the very high phonon frequencies, strong electron-phonon coupling, and therefore large critical temperatures¹⁰⁻¹⁴, the major emphasis has been given to other hydrides^{5, 15-29} such as silane^{17, 30-33}, disilane³⁴, hydrogen sulfide^{6-8, 35-41} hydrogen selenide⁹, phosphine^{42, 43}, etc.

Unfortunately, many (if not most) chemical compounds containing hydrogen only metallize at extremely high pressures. The paradigmatic case is pure hydrogen, whose metallic state is the ground-state structure only above 500 GPa⁴⁴⁻⁴⁹. There are certainly other phases that are metallic at lower pressure, but these are often thermodynamically unstable, and therefore difficult, if not impossible, to access experimentally.

A possible, but until now overlooked, solution is doping. It is well known that by introducing enough electronor hole-donating impurities one can render a semiconducting system metallic and even superconducting. This strategy was already successful in inducing superconductivity in diamond (doped with boron) in 2004⁵⁰, silicon (doped with boron⁵¹), germanium (doped with gallium⁵²), and silicon carbide (doped with boron⁵³ or aluminum⁵⁴). Transition temperatures are unfortunately rather low, remaining below 4 K.

In this work we follow this strategy, and investigate if the combination of doping and high pressure can be used to obtain high-temperature superconductivity in hydrides. We select as an example one of the most abundant, and also one of the best studied, hydrides, namely H₂O. Note that undoped H₂O remains insulating up to the terapascal range of pressures. In fact, its metallization was predicted to occur beyond 5 TPa⁵⁵⁻⁵⁸.

Results

Covalent phase of ice under pressure. Despite its simple chemical formula, H₂O appears in nature in all three common states of matter and it has one of the most complex phase diagrams known ref. 59. Over a dozen of different crystallographic phases have been reported or predicted in a wide range of temperatures and pressures⁵⁵

At ambient pressure and low temperatures ice assumes⁶⁰ its phase I, where oxygen has four hydrogen neighbors: two covalently bonded (forming the H₂O molecule) and two connected by hydrogen bonds to neighboring

¹Department of Physics, Universität Basel, Klingelbergstr. 82, 4056, Basel, Switzerland. ²Max-Planck Institut of Microstructure Physics, Weinberg 2, 06120, Halle, Germany. ³Institut für Physik, Martin-Luther-Universität Halle-Wittenberg, D-06099, Halle, Germany. Correspondence and requests for materials should be addressed to J.A.F.-L. (email: jose.flores@unibas.ch)





 $\rm H_2O$ molecules. Below 200 K, phase I transforms to phase XI, and under compression to phase IX, stable in the range from 0.1 to 1 GPa. Under further compression, and at very low temperatures, the phase VIII dominates up to 60–80 GPa. This molecular crystal can be seen as an ordered and symmetric version of phase VII that occurs at high temperatures. At 80–90 GPa emerges the cuprite-type ice-X, characterized by static, symmetric O–H bonds^{77–79}.

Figure 1 shows the calculated enthalpy for two phases of ice. In agreement with the experimental knowledge^{78,79}, we find that at low pressure phase VIII dominates. Above 110 GPa phase VIII undergoes a transition to the proton-symmetric and experimentally confirmed phase X. Benoit *et al.*⁸⁰ have shown that from 102 GPa onwards the proton-ordered symmetric ice X emerges, i.e. localized protons at the bond mid-points. At these pressures, quantum effects do not play such a crucial role as they do for the molecular "antiferroelectric" ice VIII and "paraelectric" ice VII⁸¹. Phase X is the dominant structure of ice up to 210 GPa⁸². This phase is extremely interesting from our point of view, as it is no longer a molecular crystal and exhibits a complete covalent character, as indicated by the behavior of the electron localization function⁸³ (see top panel of Fig. 1). This is absolutely essential for the appearance of doping induced superconductivity, otherwise impurities would just introduce localized states that can not participate in the formation of Cooper pairs.

Electronic structure of doped ice under pressure. In order to study doping in H₂O, we created supercells of ice X under pressure for a wide range of doping values H_2O_{1-x} Dopant_x, with x = 25%, 12.5%, 6.25%, and 4.16%. Full structural relaxation (volume and lattice vectors) were carried out for the supercells (12 atoms cell for x = 25%, 24 atoms cell for 12.5%, 48 atoms cell for 6.25% and 72 atoms cell for 4.16%) at 150 GPa. For low doping (4.16–6.25%), we find fairly small modifications of the crystal structure of ice-X. On the contrary, larger doping levels (25%) induce deformation around the N sites, even if the cuprite-type ice-X global structure is preserved.

Figure 2 depicts the electronic band structure obtained when boron, carbon, nitrogen and phosphorous are used to dope ice-X at 150 GPa. In these plots the color scale represents the overlap of the Kohn-Sham states on the atomic orbitals of the dopant: red means large overlap (dopant states dominant), gray intermediate, while blue means small (hydrogen and oxygen states dominant). For large doping with boron and phosphorous (12.5% and 25%), the dispersive band coming from the dopant completely closes the gap in ice-X, while for 4.16% and 6.25% the dopant states form impurity molecular-like bands. These atoms are therefore not suitable to hole-dope ice-X. The case of carbon is intermediate: at low doping we see again the formation of impurity bands, while at higher levels we do see some hybridization between the carbon and the ice bands at the top of the valence. In general we find a higher density of states at the Fermi level with B, C and P acting as a dopant, however the band structure shows mostly localized molecular states which are detrimental to superconductivity. It is important to mention that, since ice-X is highly symmetric (cubic structure, P - 43m, space group 215) there is only one site to substitute. A study of all possible site/defect substitutions of oxygen by dopants for high doping levels (i.e. 12.5% and 25%) is clearly beyond the scope of this work (and would probably require more advanced techniques such as



Figure 2. Electronic band structure for different dopants (B, C, N and P) in the phase-X of ice at 150 GPa. The Fermi level is set to 0 eV and the color scale represents the overlap of the Kohn-Sham states on the atomic orbitals of the dopant: red means large overlap (dopant states dominant), gray intermediate, while blue means small (hydrogen and oxygen states dominant).

| | |
|------|------|

| | Doping | | | | |
|----------------------------|--------|-------|-------|------|--|
| | 4.16% | 6.25% | 12.5% | 25% | |
| λ | 0.64 | 0.85 | 0.67 | 0.66 | |
| $\omega_{\log} ({ m meV})$ | 102 | 90 | 84 | 68 | |
| T _C (K) | 34.4 | 60.4 | 33.3 | 25.6 | |
| $\int \alpha^2 F$ (meV) | 44.2 | 51.8 | 40.4 | 34.8 | |

Table 1. Electron-phonon coupling constant (λ), logarithmic average of the phonon frequencies (ω_{log}), superconducting critical temperature (T_c) and integral of $\alpha^2 F$.

cluster expansions). However, our results provide a clear general trend of the physics of doped ice under pressure (See Table 1).

In contrast to the other dopants, nitrogen induces hole doping in ice-X (see Fig. 2) and, as shown in the Supplemental Material of ref. 84 it is also the most likely non iso-valent element able to substitute oxygen. The bottom panel in Fig. 3 shows in detail the electronic structure of ice-X: it is an insulator with a PBE electronic band gap of about 10 eV and does not undergo major modifications at least up to 300 GPa. According to our calculations, the insulator-metal transition is achievable starting from values of 4% nitrogen doping (as seen in Fig. 2). For 25% doping, the top valence is mostly dominated by nitrogen states forming a fairly dispersive band. For values between 4% and 12.5%, oxygen and nitrogen strongly hybridize in the top valence forming the metallic states (gray colors in the plot).





.....

Electronically, it is clear that nitrogen doping introduces holes in the ice X crystal. These hole states are, as intended, hybrid O–N states, as can be seen from the projected density of states in Fig. 3. At high doping (12.5% and 25%) the states at the Fermi level are homogeneous O–N hybrids, meaning that the density of N states is simply proportional to the fraction of N atoms. On the other hand, at lower doping (4.16% and 6.25%) the N projected DOS, although overall smaller, is larger than the N/O fraction and shows a sharp peak close to the Fermi level, indicating that the induced holes are more localized on the N sites. We note that the two last values are realistic and similar to the doping values used to render diamond or silicon superconducting at ambient pressure⁸⁵.

Stability of doped-ice under pressure. We studied the stability of the doped compositions with nitrogen by means of total energy DFT calculations. The top panel in Fig. 4 shows the calculated formation energy including zero point energy corrections (ZPE) for ice-X as a function of nitrogen content. The inclusion of ZPE has been show to be fundamental to describe the energetics of hydrogen-based systems, specially at high pressures^{86, 87}. Our systems lie on a straight-line drawn between H₂O and the hypothetical H₂N system.

The doped structures of ice-X are enthalpically stable towards decomposition to their elemental solids, and all the compositions lie within a mere couple of meV per formula unit above the stability line. The bottom panel zooms in the area of the ternary phase diagram under consideration in this work, solid black dots represent the ground-state enthalpy of experimentally known structures of H_2 , O_2 and N_2 occurring at 150 GPa.

We can also look at this problem from a different perspective, namely by considering N as a substitutional dopant for an oxygen atom (N_O), calculating its formation energy, and comparing it to those of intrinsic defects, such as oxygen (V_O) and hydrogen (V_H) vacancies. Figure 5 shows the calculated formation energies and enthalpies as a function of the Fermi level inside the band gap for hydrogen-rich experimental conditions. These are the most favorable conditions for V_O and hence N_O formation. The slopes in the formation energy plot indicate the stable charge state of the defect. For Fermi level values very close to the valence band maximum (relevant for hole



Figure 4. Top panel: calculated formation energy and stability line including zero point energy corrections (ZPE) for ice-X as function of nitrogen content. Bottom panel: part of the ternary phase diagram under consideration in this work, solid black dots represent the ground-state of experimentally know structures of H_2 , O_2 and N_2 occurring at 150 GPa.



Figure 5. Defect formation energies at P = 150 GPa in ice-X as a function of Fermi level for oxygen vacancy V_O , hydrogen vacancy V_H and nitrogen on a substitutional O-site N_O , under H-rich conditions. Solid lines show the calculated formation energies, while the dashed lines show the formation enthalpies (including the PV^f contribution).

conductivity) Fig. 5 indicates that the most likely defect is V_O^{+2} with N_O^0 only 1 eV higher in energy. This is a rather low value, indicating that N-doping is likely to be possible. However, our study also suggests that hole compensation by electrons provided by oxygen vacancies in ice-X cannot be ruled out. The shaded areas outline the large



Figure 6. Eliashberg spectral function (black lines) and integration curve of the electron-phonon coupling constant $\lambda(\omega)$ (red lines) for hole-doped H₂O in its phase X at 150 GPa. Doping level is indicated in each panel. Shaded areas are the projections on atomic displacements of oxygen/nitrogen (violet) and hydrogen (light blue).

impact that the inclusion of the PV^{f} term has on the formation energies at these pressures. Unfortunately, the formation volume V^{f} is not technically defined for non-elemental solids and must be approximated (see supplementary material), leading to some ambiguity in the exact values for the formation enthalpies.

Superconducting properties. There are many possible ways to study theoretically the effect of doping on the superconducting properties. The simplest way is by shifting rigidly the Fermi level, leaving both Kohn-Sham eigenvalues and eigenfunctions unchanged. The resulting phonon spectrum and electron-phonon scattering amplitude can then be used within an Eliashberg^{88, 89} scheme to compute the superconducting critical temperature as a function of the position of the Fermi level. For the ice-X of H_2O at 150 GPa we compute, within this procedure, an astonishingly high phononic superconducting coupling, leading to room-temperature superconductivity already at a doping of a few percent! Although widely used in the literature, we can not expect that such a rigid shift of the Fermi level yields more than an estimate for the order of magnitude of the critical temperature upon doping. In fact, the extreme electron-phonon coupling obtained by the rigid shift would induce a strong electronic response, leading to a complete breakdown of the rigid shift approximation. Moreover, this method does not account for important physical effects stemming from the metallic part of the electronic screening, such as the mechanism responsible for Kohn anomalies⁹⁰ that can significantly modify the spectrum of phonons.

A more realistic way to study theoretically the effect of doping on the superconducting properties is to calculate the phonon and electron-phonon matrix elements. The phonon spectra and the electron-phonon matrix elements were obtained employing density-functional perturbation theory^{91, 92}, as implemented in the plane-wave based code abinit⁹³.

As we have seen, doping turns out to have a dramatic effect on the electronic structure of ice, in the phonon spectrum (not shown) and in the Eliashberg spectral functions, shown in Fig. 6 as a function of doping at 150 GPa. Comparing the supercell calculations with results obtained with a rigidly shifted Fermi level (see Fig. 6), we observe a complete restructuring of the phonon energies and coupling strength. The metallization provides a significant screening causing both a softening of the phonon frequencies and a reduction of the deformation potential. Nevertheless we still observe a significant electron-phonon coupling, as can be seen from the Eliashberg functions as well as from the logarithmic average of the phonon frequency $\omega_{\log}^{89, 94}$ (see Fig. 7). We furthermore calculated the phonon band-structure for B, C, N, and P doping. We find that all systems are highly unstable with large imaginary frequencies, with the only exception being nitrogen, that leads to dynamically stable structures in the doping range studied.



Figure 7. Top panel: calculated critical temperatures with the McMillan-Allen-Dynes formula as a function of doping of H_2O in its phase X at 150 GPa. Lower panel: electron phonon coupling constant λ (red left triangles and left axis) and average phonon frequency ω_{\log} (green right triangles and right axis). Solid lines are a guide to the eye.

For low doping (<12.5%) two major contributions to λ can be distinguished: (i) the low frequency optical phonons (oxygen vibrations) that couple with 2*p* nitrogen states; and (ii) the mid-frequency range 150–200 meV (1100–1800 cm⁻¹) that couples with the covalent oxygen-nitrogen hybridized state. For 25% doping all phonon branches contribute significantly to the *e* – *p* coupling, since at this doping the structure adopts a completely metallic character.

From these parameters we can easily estimate the critical temperature by means of the McMillan-Allen-Dynes⁹⁵ formula. This gives T_C in the range from 20 to 60 K (assuming $\mu^* = 0.1$), with the maximum value reached for a doping level of 6.25% (see Fig. 7). Although lower than the astonishing value found in sulphur hydride (200 K) and considerably lower than the rigid shift prediction (300 K) this is still a sizable value, much larger than the $T_C \lesssim 4$ K found in doped semiconductors at ambient pressure.

Discussion

We now turn to the question of how one could synthesize the doped phase of ice under pressure. One possible path is to use a high pressure synthesis similar to the one used to obtain H_2+H_2O clathrates⁷¹. This involves inserting, at room temperature, H_2 molecules inside the H_2O crystalline C_1 (clathrate) phase of water at 0.7 GPa. Experimentally, the unit cell of the C_1 phase contains 36 water molecules in a channel-like arrangement, which can host up to six hydrogen molecules^{96, 97}. One could start the synthesis with the analogous N_2+H_2O clathrate (C_1), where the percentage of filled N_2 molecules will determine the doping level at high pressure⁹⁸. However, it is well-known that N_2 is one of the most stable molecules in the universe. Therefore, following this path would require high energies to break the strong N–N covalent bond, achievable perhaps only with strong laser heating.

Another possibility is to start with a less stable molecule, such as ammonia (NH₃). The stability of ammonia is greatly reduced under pressure, and indeed it has been reported that it forms super-ionic phases⁹⁹. These compositions have been extensively studied and well documented, however, only up to relatively low pressures of 50 GPa¹⁰⁰.

A third possibility is to start the synthesis with admixtures of other molecules, such as nitric oxide (NO), nitrogen dioxide (NO₂) or azanide H_2N to name a few. Unfortunately, all of these mixtures have been scarcely studied at high pressure.

In conclusion, we investigated the possibility of inducing high-temperature superconductivity by doping insulating hydrides under pressure. By taking the phase X of ice as an example, we studied how the phonon spectra and the electron-phonon coupling evolve as a function of doping. Several dopants were analyzed, with the conclusion that only nitrogen leads to dynamically stable structures that are hole-doped. It turns out that for rather reasonable values of doping, one can reach superconducting transition temperatures as high as 60 K at 150 GPa. Considering the vast number of hydrides that remain insulating under pressure and that can be doped, this result opens a number of possibilities for the exploration of high-temperature superconductivity in these systems.

Methods

The energies, atomic forces and stresses were evaluated within density functional theory with the Perdew-Burke-Erzernhof (PBE)¹⁰¹ approximation to the exchange-correlation functional. A plane wave basis-set with a high cutoff energy of 1000 eV was used to expand the wave-functions together with the projector augmented wave (PAW) method as implemented in the Vienna Ab Initio Simulation Package vasp¹⁰². Geometry relaxations were performed with tight convergence criteria such that the forces on the atoms were less than 2 meV/Å and the stresses were less than 0.1 meV/Å^3 .

The reference structures for hydrogen are $P6_3m$ (0–120 GPa) and C2/c (120–300 GPa) from ref. 45. The reference phase for oxygen is C2/m, ζ structure^{103–105}.

The phonon spectra and the electron-phonon matrix elements were obtained with density-functional perturbation theory^{91,92}, as implemented in the plane-wave based code abinit⁹³. For the electron-phonon the following *k* and *q*-meshes were used for the different supercells: 25% doping, $k = 16 \times 16 \times 16$, and $q = 8 \times 8 \times 8$; 12.5%

doping, $k = 8 \times 8 \times 8$ and $q = 4 \times 4 \times 4$; 6.25% doping, $k = 4 \times 4 \times 4$ and $q = 4 \times 4 \times 4$; 4.16% doping, $k = 2 \times 2 \times 2$ and $q = 2 \times 2 \times 2$.

For defect formation energy calculations we used $k = 2 \times 2 \times 2$. Formation energies for oxygen (V_0) and hydrogen (V_H) vacancies were calculated using the standard formulation.

$$E^{f} = E_{D}^{q} - E_{H_{2}O} - \sum_{i} n_{i} [\mu_{i} + \Delta \mu_{i}] + q[\varepsilon_{VBM} + \Delta \varepsilon_{F}] + E_{cor}$$
(1)

where E_D^q is the energy of a supercell, here $3 \times 3 \times 3$, containing a vacancy D in a charge state q, $E_{\rm H_2O}$ is the energy of the same size pure crystal supercell, n_i is the number of elements added to the supercell and μ_i is the chemical potential of an element *i* defined as the energy per atom of the reference phase (for H₂, N₂ and O₂ the stable phases at 150 GPa were used). The quantity $\Delta \mu_i$ is dependent on the experimental conditions, but can be viewed as a free parameter bound by the stability of the crystal ice phase. Finally, $\varepsilon_{\rm VBM}$ is the energy of the valence band minimum (VBM) of the pure crystal, $\Delta \varepsilon_F$ is the value of the Fermi level referenced to the VBM, and $E_{\rm cor}$ is the electrostatic correction energy, including an alignment term, calculated using the SXDEFECTALIGN code¹⁰⁶. All formation energy calculations were performed including local atomic environment relaxations only. Formation enthalpies were obtained using Eq. 2, where $E_{\rm relax}^f$ is calculated via Eq. 1 with volume relaxations in the calculation of supercell energies.

$$H^f = E^f_{\text{relax}} + PV^f \tag{2}$$

The dielectric constant used for electrostatic corrections included both the static dielectric and the ionic contributions. We did not considered changes in the electrostatic energy with the relaxation volume.

References

- 1. Duan, D. et al. Pressure-induced metallization of dense (h2s)2h2 with high-tc superconductivity. Sci. Rep. 4, 6968 (2014).
- Drozdov, A. P., Eremets, M. I., Troyan, I. A., Ksenofontov, V. & Shylin, S. I. Conventional superconductivity at 203 kelvin at high pressures in the sulfur hydride system. *Nature* 525, 73, doi:10.1038/nature14964 (2015).
- Bardeen, J., Cooper, L. N. & Schrieffer, J. R. Theory of superconductivity. *Phys. Rev.* 108, 1175–1204, doi:10.1103/PhysRev.108.1175 (1957).
- 4. Mazin, I. I. Superconductivity: Extraordinarily conventional. Nature 525, 40-41 (2015).
- Muramatsu, T. et al. Metallization and superconductivity in the hydrogen-rich ionic salt bareh9. J. Phys. Chem. C 119, 18007–18013, doi:10.1021/acs.jpcc.5b03709 (2015).
- Bernstein, N., Hellberg, C. S., Johannes, M. D., Mazin, I. I. & Mehl, M. J. What superconducts in sulfur hydrides under pressure and why. *Phys. Rev. B* 91, 060511, doi:10.1103/PhysRevB.91.060511 (2015).
- 7. Duan, D. et al. Pressure-induced decomposition of solid hydrogen sulfide. Phys. Rev. B 91, 180502, doi:10.1103/ PhysRevB.91.180502 (2015).
- Heil, C. & Boeri, L. Influence of bonding on superconductivity in high-pressure hydrides. *Phys. Rev. B* 92, 060508, doi:10.1103/ PhysRevB.92.060508 (2015).
- 9. Flores-Livas, A. J., Sanna, A. & Gross, E. High temperature superconductivity in sulfur and selenium hydrides at high pressure. *Eur. Phys. J. B* **89**, 1–6, doi:10.1140/epjb/e2016-70020-0 (2016).
- Ashcroft, N. Metallic hydrogen: A high-temperature superconductor? *Phys. Rev. Lett.* 21, 1748–1749, doi:10.1103/ PhysRevLett.21.1748 (1968).
- Richardson, C. F. & Ashcroft, N. W. High temperature superconductivity in metallic hydrogen: Electron-electron enhancements. *Phys. Rev. Lett.* 78, 118–121, doi:10.1103/PhysRevLett.78.118 (1997).
- 12. Cudazzo, P. *et al.* Ab Initio description of high-temperature superconductivity in dense molecular hydrogen. *Phys. Rev. Lett.* **100**, 257001, doi:10.1103/PhysRevLett.100.257001 (2008).
- McMahon, J. M. & Ceperley, D. M. High-temperature superconductivity in atomic metallic hydrogen. *Phys. Rev. B* 84, 144515, doi:10.1103/PhysRevB.84.144515 (2011).
- McMahon, J. M. & Ceperley, D. M. Erratum: High-temperature superconductivity in atomic metallic hydrogen [phys. rev. b 84, 144515 (2011)]. Phys. Rev. B 85, 219902(E), doi:10.1103/PhysRevB.85.219902 (2012).
- Ashcroft, N. W. Hydrogen dominant metallic alloys: High temperature superconductors? *Phys. Rev. Lett.* 92, 187002, doi:10.1103/ PhysRevLett.92.187002 (2004).
- Tse, J. S., Yao, Y. & Tanaka, K. Novel Superconductivity in Metallic SnH₄ under High Pressure. *Phy. Rev. Lett.* 98, 117004, doi:10.1103/PhysRevLett.98.117004 (2007).
- 17. Chen, X.-J. et al. Pressure-induced metallization of silane. Proc. Natl. Acad. Sci. USA 105, 20–23, doi:10.1073/pnas.0710473105 (2008).
- Kim, D. Y. *et al.* Crystal structure of the pressure-induced metallic phase of sih4 from ab initio theory. *Proc. Natl. Acad. Sci. USA* 105, 16454–16459, doi:10.1073/pnas.0804148105 (2008).
- Feng, J., Hennig, R. G., Ashcroff, N. W. & Hoffmann, R. Emergent reduction of electronic state dimensionality in dense ordered Li-Be alloys. *Nature* 451, 445–448, doi:10.1038/nature06442 (2008).
- Wang, S., Mao, H.-K., Chen, X.-J. & Mao, W. L. High pressure chemistry in the h2-sih4 system. Proc. Natl. Acad. Sci. USA 106, 14763–14767, doi:10.1073/pnas.0907729106 (2009).
- Yao, Y. & Klug, D. D. Silane plus molecular hydrogen as a possible pathway to metallic hydrogen. Proc. Natl. Acad. Sci. USA 107, 20893–20898, doi:10.1073/pnas.1006508107 (2010).
- Gao, G. et al. High-pressure crystal structures and superconductivity of Stannane (SnH₄). Proc. Natl. Acad. Sci. USA 107, 1317–1320, doi:10.1073/pnas.0908342107 (2010).
- Kim, D. Y., Scheicher, R. H., Mao, H.-K., Kang, T. W. & Ahuja, R. General trend for pressurized superconducting hydrogen-dense materials. Proc. Natl. Acad. Sci. USA 107, 2793–2796, doi:10.1073/pnas.0914462107 (2010).
- Li, Y. et al. Superconductivity at 100 k in dense sih₄ (h₂)₂ predicted by first principles. Proc. Natl. Acad. Sci. USA 107, 15708–15711, doi:10.1073/pnas.1007354107 (2010).
- Zhou, D. et al. Ab initio study revealing a layered structure in hydrogen-rich kh₆ under high pressure. Phys. Rev. B 86, 014118, doi:10.1103/PhysRevB.86.014118 (2012).
- Hooper, J., Terpstra, T., Shamp, A. & Zurek, E. Composition and constitution of compressed strontium polyhydrides. *The Journal of Physical Chemistry C* 118, 6433–6447, doi:10.1021/jp4125342 (2014).
- 27. Esfahani, M. M. D. et al. Superconductivity of novel tin hydrides (snnhm) under pressure. Scientific reports 6 (2016).
- 28. Struzhkin, V. V. et al. Synthesis of sodium polyhydrides at high pressures. arXiv preprint arXiv:1412.1542 (2014).

- Zhong, X. et al. Tellurium hydrides at high pressures: High-temperature superconductors. Phys. Rev. Lett. 116, 057002, doi:10.1103/ PhysRevLett.116.057002 (2016).
- Eremets, M. I., Trojan, I. A., Medvedev, S. A., Tse, J. S. & Yao, Y. Superconductivity in hydrogen dominant materials: Silane. Science 319, 1506–1509, doi:10.1126/science.1153282 (2008).
- Degtyareva, O., Proctor, J. E., Guillaume, C. L., Gregoryanz, E. & Hanfland, M. Formation of transition metal hydrides at high pressures. *Solid State Commun.* 149, 1583–1586, doi:10.1016/j.ssc.2009.07.022 (2009).
- Hanfland, M., Proctor, J. E., Guillaume, C. L., Degtyareva, O. & Gregoryanz, E. High-pressure synthesis, amorphization, and decomposition of silane. *Phy. Rev. Lett.* 106, 095503, doi:10.1103/PhysRevLett.106.095503 (2011).
- Strobel, T. A., Ganesh, P., Somayazulu, M., Kent, P. R. C. & Hemley, R. J. Novel cooperative interactions and structural ordering in h₂S-h₂. Phys. Rev. Lett. 107, 255503, doi:10.1103/PhysRevLett.107.255503 (2011).
- Flores-Livas, J. A. et al. High-pressure structures of disilane and their superconducting properties. Phys. Rev. Lett. 108, 117004, doi:10.1103/PhysRevLett.108.117004 (2012).
- 35. Errea, I. *et al.* Quantum hydrogen-bond symmetrization in the superconducting hydrogen sulfide system. *Nature* **532**, 81–84 (2016).
- Errea, I. et al. High-pressure hydrogen sulfide from first principles: A strongly anharmonic phonon-mediated superconductor. Phys. Rev. Lett. 114, 157004, doi:10.1103/PhysRevLett.114.157004 (2015).
- Akashi, R., Kawamura, M., Tsuneyuki, S., Nomura, Y. & Arita, R. First-principles study of the pressure and crystal-structure dependences of the superconducting transition temperature in compressed sulfur hydrides. *Phys. Rev. B* 91, 224513, doi:10.1103/ PhysRevB.91.224513 (2015).
- Quan, Y. & Pickett, W. E. Impact of van Hove singularities in the strongly coupled high temperature superconductor H3s. arXiv: 1508.04491 [cond-mat.supr-con] (2015).
- Xie, Y., Li, Q., Oganov, A. R. & Wang, H. Superconductivity of lithium-doped hydrogen under high pressure. Acta Crystallographica Section C: Structural Chemistry 70, 104–111 (2014).
- Ortenzi, L., Cappelluti, E. & Pietronero, L. Band Structure and electron-phonon coupling in H₃S: a tight-binding model. *arXiv*: 1511.04304 [cond-mat.mtrl-sci] (2015).
- Akashi, R., Sano, W., Arita, R. & Tsuneyuki, S. Possible "magnéli" phases and self-alloying in the superconducting sulfur hydride. *Phys. Rev. Lett.* 117, 075503, doi:10.1103/PhysRevLett.117.075503 (2016).
- Drozdov, A., Eremets, M. I. & Troyan, I. A. Superconductivity above 100 K in PH3 at high pressures. arXiv: 1508.06224 [cond-mat.supr-con] (2015).
- Flores-Livas, J. A. et al. Superconductivity in metastable phases of phosphorus-hydride compounds under high pressure. Phys. Rev. B 93, 020508, doi:10.1103/PhysRevB.93.020508 (2016).
- 44. Wigner, E. & Huntington, H. B. On the possibility of a metallic modification of hydrogen. J. Chem. Phys. 3, 764-770, doi:10.1063/1.1749590 (1935).
- 45. Pickard, C. J. & Needs, R. J. Structure of phase III of solid hydrogen. Nat. Phys. 3, 473-476, doi:10.1038/nphys625 (2007).
- Loubeyre, P., Occelli, F. & LeToullec, R. Optical studies of solid hydrogen to 320 GPa and evidence for black hydrogen. Nature 416, 13–17, doi:10.1038/416613a (2002).
- Eremets, M. I. & Troyan, I. A. Conductive dense hydrogen. Nat. Mat. 10, 927–931, URL http://www.nature.com/nmat/journal/v10/ n12/abs/nmat3175.html#supplementary-information, doi:10.1038/nmat3175 (2011).
- Zha, C.-S., Liu, Z. & Hemley, R. J. Synchrotron infrared measurements of dense hydrogen to 360 gpa. Phys. Rev. Lett. 108, 146402, doi:10.1103/PhysRevLett.108.146402 (2012).
- Naumov, I. I. & Hemley, R. J. Aromaticity, closed-shell effects, and metallization of hydrogen. Acc. Chem. Res. 47, 3551–3559, doi:10.1021/ar5002654 (2014).
- Ekimov, E. A. et al. Superconductivity in diamond. Nature 428, 542–545, http://www.nature.com/nature/journal/v428/n6982/abs/ nature02449.html, doi:10.1038/nature02449 (2004).
- 51. Bustarret, E. et al. Superconductivity in doped cubic silicon. Nature 444, 465-468 (2006).
- 52. Herrmannsdörfer, T. *et al.* Superconducting state in a gallium-doped germanium layer at low temperatures. *Phys. Rev. Lett.* **102**, 217003, doi:10.1103/PhysRevLett.102.217003 (2009).
- 53. Kriener, M. *et al.* Superconductivity in heavily boron-doped silicon carbide. *Sci. Technol. Adv. Mater.* 9, 044205, doi:10.1088/1468-6996/9/4/044205 (2008).
- Muranaka, T., Kikuchi, Y., Yoshizawa, T., Shirakawa, N. & Akimitsu, J. Superconductivity in carrier-doped silicon carbide. Sci. Technol. Adv. Mater. 9, 044204, doi:10.1088/1468-6996/9/4/044204 (2008).
- 55. Militzer, B. & Wilson, H. F. New phases of water ice predicted at megabar pressures. Phys. Rev. Lett. 105, 195701 (2010).
- McMahon, J. M. Ground-state structures of ice at high pressures from ab initio random structure searching. *Phys. Rev. B* 84, 220104 (2011).
- Zhang, S., Wilson, H. F., Driver, K. P. & Militzer, B. H₄o and other hydrogen-oxygen compounds at giant-planet core pressures. *Phys. Rev. B* 87, 024112, doi:10.1103/PhysRevB.87.024112 (2013).
- Pickard, C. J., Martinez-Canales, M. & Needs, R. J. Decomposition and terapascal phases of water ice. *Phys. Rev. Lett.* 110, 245701, doi:10.1103/PhysRevLett.110.245701 (2013).
- 59. Bartels-Rausch, T. et al. Ice structures, patterns, and processes: A view across the icefields. Rev. Mod. Phys. 84, 885 (2012).
- 60. Bjerrum, N. Structure and properties of ice. Science 115, 385-390 (1952).
- 61. Kamb, B. Ice. ii. a proton-ordered form of ice. Acta Crystallogr. 17, 1437-1449 (1964).
- 62. Londono, J., Kuhs, W. & Finney, J. Neutron diffraction studies of ices iii and ix on under-pressure and recovered samples. J. Chem. Phys. 98, 4878–4888 (1993).
- 63. Whalley, E., Heath, J. & Davidson, D. Ice ix: an antiferroelectric phase related to ice iii. J. Chem. Phys. 48, 2362-2370 (1968).
- Kuhs, W., Finney, J., Vettier, C. & Bliss, D. Structure and hydrogen ordering in ices vi, vii, and viii by neutron powder diffraction. J. Chem. Phys. 81, 3612–3623 (1984).
- 65. Kamb, B., Prakash, A. & Knobler, C. Structure of ice. v. Acta Crystallogr. 22, 706-715 (1967).
- Salzmann, C. G., Radaelli, P. G., Hallbrucker, A., Mayer, E. & Finney, J. L. The preparation and structures of hydrogen ordered phases of ice. *Science* 311, 1758–1761 (2006).
- 67. Jorgensen, J. D. & Worlton, T. G. Disordered structure of d20 ice vii from *insitu* neutron powder diffraction. J. Chem. Phys. 83, 329–333 (1985).
- Besson, J. M. et al. Variation of interatomic distances in ice viii to 10 gpa. Phys. Rev. B 49, 12540–12550, doi:10.1103/ PhysRevB.49.12540 (1994).
- 69. Hemley, R. et al. Static compression of h2o-ice to 128 gpa (1.28 mbar). Nature 330, 737-740 (1987).
- Goncharov, A. F. et al. Dynamic ionization of water under extreme conditions. Phys. Rev. Lett. 94, 125508, doi:10.1103/ PhysRevLett.94.125508 (2005).
- Vos, W. L., Finger, L. W., Hemley, R. J. & Mao, H.-K. Novel h₂-h₂o clathrates at high pressures. *Phys. Rev. Lett.* 71, 3150–3153, doi:10.1103/PhysRevLett.71.3150 (1993).
- Mishima, O. Reversible first-order transition between two h2o amorphs at 0.2 gpa and 135 k. J. Chem. Phys 100, 5910–5912 (1994).
 Loerting, T., Salzmann, C., Kohl, I., Mayer, E. & Hallbrucker, A. A second distinct structural "state" of high-density amorphous ice
- at 77 k and 1 bar. Phys. Chem. Chem. Phys. 3, 5355–5357 (2001).

- 74. Smith, R. S. & Kay, B. D. The existence of supercooled liquid water at 150 k. Nature 398, 788-791 (1999).
- 75. Angell, C. A. Amorphous water. Annu. Rev. Phys. Chem. 55, 559-583 (2004).
- Yen, F., Chi, Z., Berlie, A., Liu, X. & Goncharov, A. F. Dielectric anomalies in crystalline ice: Indirect evidence of the existence of a liquid–liquid critical point in h2o. J. Phys. Chem. C 119, 20618–20622 (2015).
- 77. Holzapfel, W. On the symmetry of the hydrogen bonds in ice vii. The Journal of Chemical Physics 56, 712-715 (1972).
- Pruzan, P., Chervin, J. & Canny, B. Stability domain of the ice viii proton-ordered phase at very high pressure and low temperature. *The Journal of chemical physics* 99, 9842–9846 (1993).
- 79. Pruzan, P. Pressure effects on the hydrogen bond in ice up to 80 gpa. Journal of molecular structure 322, 279-286 (1994).
- 80. Benoit, M., Marx, D. & Parrinello, M. Tunnelling and zero-point motion in high-pressure ice. Nature 392, 258-261 (1998).
- Benoit, M., Marx, D. & Parrinello, M. The role of quantum effects and ionic defects in high-density ice. Solid State Ionics 125, 23–29 (1999).
- Goncharov, A., Struzhkin, V., Somayazulu, M., Hemley, R. & Mao, H. Compression of ice to 210 gigapascals: Infrared evidence for a symmetric hydrogen-bonded phase. *Science* 273, 218 (1996).
- Becke, A. D. & Edgecombe, K. E. A simple measure of electron localization in atomic and molecular systems. J. Chem. Phys. 92, 5397–5403, doi:10.1063/1.458517 (1990).
- Glawe, H., Sanna, A., Gross, E. K. U. & Marques, M. A. L. The optimal one dimensional periodic table: a modified pettifor chemical scale from data mining. *New Journal of Physics* 18, 093011 (2016).
- Blase, X. Superconductivity in doped clathrates, diamond and silicon. C. R. Phys. 12, 584–590, doi:10.1016/j.crhy.2011.03.002 (2011).
- Hermann, A., Ashcroft, N. W. & Hoffmann, R. Isotopic differentiation and sublattice melting in dense dynamic ice. *Phys. Rev. B* 88, 214113, doi:10.1103/PhysRevB.88.214113 (2013).
- Liu, H., Yao, Y. & Klug, D. D. Stable structures of he and h₂O at high pressure. *Phys. Rev. B* 91, 014102, doi:10.1103/ PhysRevB.91.014102 (2015).
- 88. Eliashberg, G. Eliashberg Equations of Strong Coupling Theory. Teor. Fiz. 38 (1960); Sov. Phys. FETP 11, 696 (1960).
- 89. Allen, P. B. & Mitrović, B. Theory of Superconducting Tc, vol. 37 of Solid State Physics (Academic Press, 1983).
- Kohn, W. Image of the fermi surface in the vibration spectrum of a metal. *Phys. Rev. Lett.* 2, 393-394, doi:10.1103/ PhysRevLett.2.393 (1959).
- Baroni, S., Giannozzi, P. & Testa, A. Green's-function approach to linear response in solids. *Phys. Rev. Lett.* 58, 1861–1864, doi:10.1103/PhysRevLett.58.1861 (1987).
- Gonze, X. & Vigneron, J.-P. Density-functional approach to nonlinear-response coefficients of solids. *Phys. Rev. B* 39, 13120–13128, doi:10.1103/PhysRevB.39.13120 (1989).
- Gonze, X. et al. ABINIT: first-principles approach to material and nanosystem properties. Comput. Phys. Commun. 180, 2582–2615 (2009).
- Carbotte, J. P. Properties of boson-exchange superconductors. *Rev. Mod. Phys.* 62, 1027–1157, doi:10.1103/RevModPhys.62.1027 (1990).
- Allen, P. B. & Dynes, R. C. Transition temperature of strong-coupled superconductors reanalyzed. *Phys. Rev. B* 12, 905–922, doi:10.1103/PhysRevB.12.905 (1975).
- Smirnov, G. S. & Stegailov, V. V. Toward determination of the new hydrogen hydrate clathrate structures. *The Journal of Physical Chemistry Letters* 4, 3560–3564, doi:10.1021/jz401669d (2013).
- 97. Qian, G.-R., Lyakhov, A. O., Zhu, Q., Oganov, A. R. & Dong, X. Novel hydrogen hydrate structures under pressure. *Scientific reports* 4 (2014).
- Strobel, T. A., Somayazulu, M. & Hemley, R. J. Phase behavior of H₂+H₂O at high pressures and low temperatures. *The Journal of Physical Chemistry C* 115, 4898–4903, doi:10.1021/jp1122536 (2011).
- 99. Ninet, S. *et al.* Experimental and theoretical evidence for an ionic crystal of ammonia at high pressure. *Phys. Rev. B* **89**, 174103, doi:10.1103/PhysRevB.89.174103 (2014).
- 100. Jiang, X., Wu, X., Zheng, Z., Huang, Y. & Zhao, J. Ionic and superionic phases in ammonia dihydrate Nh₃ · 2h₂O under high pressure. *Phys. Rev. B* 95, 144104, doi:10.1103/PhysRevB.95.144104 (2017).
- 101. Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized gradient approximation made simple. Phys. Rev. Lett. 77, 3865–3868 (1996).
- Kresse, G. & Furthmüller, J. Efficiency of ab-initio total energy calculations for metals and semiconductors using a plane-wave basis set. Comput. Mat. Sci. 6, 15–50 (1996).
- 103. Ma, Y., Oganov, A. R. & Glass, C. W. Structure of the metallic ζ -phase of oxygen and isosymmetric nature of the ε - ζ phase transition: *Ab initio* simulations. *Phys. Rev. B* **76**, 064101, doi:10.1103/PhysRevB.76.064101 (2007).
- 104. Ochoa-Calle, A. J., Zicovich-Wilson, C. M. & Ramrez-Sols, A. Solid oxygen ζ phase and its transition from ε phase at extremely high pressure: A first-principles analysis. *Phys. Rev. B* 92, 085148, doi:10.1103/PhysRevB.92.085148 (2015).
- Weck, G., Desgreniers, S., Loubeyre, P. & Mezouar, M. Single-crystal structural characterization of the metallic phase of oxygen. *Phys. Rev. Lett.* **102**, 255503, doi:10.1103/PhysRevLett.102.255503 (2009).
- Freysoldt, C., Neugebauer, J. & Van de Walle, C. G. Fully ab initio finite-size corrections for charged-defect supercell calculations. *Physical review letters* 102, 016402 (2009).
- 107. Goncharov, A. F., Struzhkin, V. V., Mao, H.-K. & Hemley, R. J. Raman spectroscopy of dense h₂O and the transition to symmetric hydrogen bonds. *Phys. Rev. Lett.* 83, 1998–2001, doi:10.1103/PhysRevLett.83.1998 (1999).

Acknowledgements

J.A.F.-L. warm thanks Prof. Roald Hoffmann for fruitful discussions in Cornell and acknowledges computational resources under the project (s707 and s752) from the Swiss National Supercomputing Center (CSCS) in Lugano. M.A.L.M. acknowledges partial support from the DFG through projects SFB-762 and MA 6787/1-1.

Author Contributions

J.A.F.-L., A.S. and M.A.L.M. conceived the main idea of the research project. J.A.F.-L., A.S., A.D. and M.G. executed the calculations. J.A.F.-L., A.S., M.G., A.D., S.G. and M.A.L.M. analyzed the results, wrote and reviewed the manuscript.

Additional Information

Supplementary information accompanies this paper at doi:10.1038/s41598-017-07145-4

Competing Interests: The authors declare that they have no competing interests.

Publisher's note: Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons license, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons license and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this license, visit http://creativecommons.org/licenses/by/4.0/.

© The Author(s) 2017